



SECTION 09 24 23
Arisfor WallGuard®

1.1 GENERAL

- A. Arisfor WallGuard® is a three component polymerized cementitious protective coating that can be applied to a variety of vertical interior and exterior substrates including: stucco, exterior gypsum sheathing, ICF blocks, masonry, concrete, wood, metal and tile. Arisfor WallGuard® has superior adhesive properties and is extremely durable. This unique coating is abrasion resistant, impact resistant and water resistant while allowing for transmission of moisture vapor from substrate.
- B. It is the responsibility of both the specifiers and the purchaser to determine if a product is suitable for its intended use. The designer selected by the purchaser shall be responsible for all decisions pertaining to design, details structural integrity, attachment details, shop drawings and etc.
- C. Furnishing and installing metal flashings, drains, vents, ducts, curbs, expansion joints or any RELATED SECTIONS
 - 1. Section 03 30 00 - Cast-in-Place Concrete.
 - 2. Section 03 41 16 - Precast Concrete Slabs.
 - 3. Section 04 20 00 - Unit Masonry.
 - 4. Section 05 40 00 – Cold Form Metal Framing
 - 5. Section 06 11 16 - Mechanically Graded Lumber.
 - 6. Section 06 16 36 - Wood Panel Product Sheathing.
 - 7. Section 07 62 00 – Sheet Metal Flashing and Trim.
 - 8. Section 07 90 00 – Joint Protection.
 - 9. Section 07 91 26 - Joint Fillers.
 - 10. Section 09 90 00 - Painting and Coating.

1.2 REFERENCES

- A. ACI (American Concrete Institute).
- B. ASTM International (ASTM):
 - 1. ASTM C 150 - Standard Specification for Portland Cement.
 - 2. ASTM C 847 - Standard Specification for Metal Lath.
 - 3. ASTM C 920 - Standard Specification for Elastomeric Joint Sealants.
 - 4. ASTM C 926 - Standard Specification for Application of Portland Cement Based Plaster.
 - 5. ASTM C 979 - Standard Specification for Pigments for Integrally Colored Concrete.
 - 6. ASTM C 1059 - ASTM C1059/C1059M-13 Standard Specification for Latex Agents for Bonding Fresh To Hardened Concrete
 - 7. ASTM C 1063 - Standard Specification for Installation of Lathing and Furring for Portland Cement Plaster.
 - 8. ASTM E 1042 - 02 Standard Classification for Acoustically Absorptive Materials Applied



SECTION 09 24 23
Arisfor WallGuard®

by Trowel or Spray
9. ICC (International Code Council).

- C. NWCB (NW Wall & Ceiling Bureau) - Stucco Resource Guide.
- D. PCA (Portland Cement Association).
- E. NCMA TR-88 - Hot & Cold Weather Masonry Construction Manual.
- F. MPI (Master Painters Institute)

1.3 SUBMITTALS

- A. Submit under provisions of Section 01 30 00 - Administrative Requirements.
- B. Product Data: Manufacturer's fact data sheets on each product to be used, including:
 - 1. Mixing and preparation instructions and recommendations.
 - 2. Storage and handling requirements and recommendations.
 - 3. Installation methods.
 - 4. Material Safety Data Sheet.
 - 5. Certificate of Completion – Arisfor® Training
- C. LEED Submittals:
Product Certificates for Credit MR 5: For products and materials required to comply with requirements for regional materials, certificates indicating location of material manufacturer and point of extraction, harvest, or recovery for each raw material. Include statement indicating distance to Project, cost for each regional material, and fraction by weight that is considered regional.
- D. Selection Samples: For each finish product specified, two complete sets of color chips representing manufacturer's full range of available colors.
- E. Verification Samples: For each finish product specified, two samples, minimum size 6 inches (150 mm) long representing actual product, in color selected.

1.4 PREFORMANCE REQUIREMENTS

- A. Testing Results

Test	Method	Results
Chemical Resistance	ASTM D 1308	No Surface Deterioration
Scrub Resistance	ASTM D 2486	At 10,000 scrub cycles: no signs of deterioration or wear
Resistance of Organic	ASTM D 2794	No cracking an 270 inch-pounds



SECTION 09 24 23
Arisfor WallGuard®

Coating to the Effect of Rapid Deformation (Impact)		
Test	Method	Results
Adhesive/Cohesive Strength	ASTM D 4541	406 psi
Wind-Driven Rain for Exterior Coatings Applied on Masonry	ASTM D 6904	0.11 lbs
Pull-off Adhesion Strength of Coatings on Concrete	ASTM D 7234	222 psi
Fire Test	ASTM E 84	Flame Spread Index 5 Smoke Developed Value 10
Water Vapor Transmission of Material	ASTM E 96	11.99 grains/h-ft ² Hg
Accelerated Weathering	ASTM G 26	No blistering, cracking, checking, adhesion loss or degradation.

1.5 QUALITY ASSURANCE

- A. Manufacturer Qualifications: Firm specializing in manufacture of masonry materials with minimum 10 years' experience.
- B. Installer Qualifications: Minimum 5 year experience installing similar products.
- C. Mock-Up: Provide a mock-up for evaluation of surface preparation techniques and application workmanship.
 - 1. Finish areas designated by Architect/Engineer.
 - 2. Do not proceed with remaining work until Architect/Engineer approves workmanship.
 - 3. Refinish mock-up area as required to produce acceptable work.

1.6 PRE-INSTALLATION MEETINGS

- A. Pre-Installation Meeting: At least three weeks prior to commencing work conduct a meeting at the project site to discuss contract requirements and job conditions
- B. Require the attendance of Owner, Architect/Engineer, Project Manager's, Plastering Contractor and/or Installers of related materials.
- C. Notify Architect/Engineer in advance of meeting.

1.7 DELIVERY, STORAGE, AND HANDLING

- A. Deliver Arisfor WallGuard® components to site in manufacturer's original unopened sealed bags and containers with labels clearly indicating manufacturer and material.



SECTION 09 24 23
Arisfor WallGuard®

- B. Store materials indoors in an area protected from freezing, excessive heat and damage. Refer to "Store Materials" ASTM C 926.
- C. Any damaged materials must be replaced.

1.8 PROJECT CONDITIONS

- A. Do not apply when air or substrate temperature is below 40 degrees F (4 degrees C).
- B. Do not apply to frozen substrate or to a substrate containing frost.
- C. Remove all loose paint, chipped concrete or other loose materials.
- D. Remove all oil and grease from surface.
- E. Application must comply with referenced standards and manufacturer's published recommendations.
- F. Do not store or apply materials when temperatures are below 40 degrees F (4 degrees C) or above 90 degrees F (32 degrees C).
- G. Protect from uneven and excessive evaporation during dry weather and from strong blasts of dry air.

1.9 SEQUENCING

- A. Ensure that products of this section are supplied to affected trades in time to prevent interruption of construction progress.

PART 2 PRODUCTS

2.1 MANUFACTURERS

- A. Acceptable Manufacturer: Arisfor®, which is located at: 100 Forta Drive; Grove City, PA 16127-6399; Toll Free Tel: 800-245-0306; Tel: 724-458-5221; Fax: 724-458-8331; Web:www.Arisfor.com

Representative: Mark Hubert – National Sales Manager
100 Forta Dive, Grove City PA 16127-6399
Tel: 401-965-3206
mhubert@fortakote.com

- B. Substitutions: Not permitted.

2.2 MATERIAL

- A. Arisfor WallGuard®: Portland cement stucco by Arisfor® comprised of the following base finish materials:
 1. Arisfor® Bond (liquid component) Six (6) gallon pail
 2. Arisfor WallGuard® (cement based component) 50-lb bags.
 3. Arisfor® Mesh (fiberglass mesh component) 475 sq. ft. roll (38 inches x 150 ft.



SECTION 09 24 23
Arisfor WallGuard®

2.3 MIXING

- A. Mixing Procedure: Follow product mixing instructions from technical data sheets
- B. Re-tempering: Use Arisfor WallGuard® system cement plaster within 1 hour of initial mixing.
- C. Hot Weather: Follow National Concrete Masonry Association recommendations for hot weather construction.
- D. Cold Weather: Follow National Concrete Masonry Association recommendations for cold weather construction.

PART 3 EXECUTION

3.1 EXAMINATION

- A. Do not begin installation until substrates have been properly prepared.
- B. If substrate preparation is the responsibility of another installer, notify Architect/Engineer of unsatisfactory preparation. Corrections of the substrate must be made before proceeding.

3.2 PREPARATION

- A. Clean surfaces thoroughly prior to installation. All surfaces that are to be coated with Arisfor WallGuard® must be sound and free from any bond obstructing substances such as loose debris, grease, oil and any other contaminants or impeding materials.
- B. Prepare surfaces in accordance with ASTM C 926 and products published information in the fact data sheet.
- C. Prepare surfaces using the methods recommended by the manufacturer for achieving the best result for the substrate under the project conditions.

3.3 INSTALLATION

- A. Install in accordance with manufacturer's instructions per the Arisfor® Fact Data Sheet and in accordance applicable IBC, IRC, ASTM, ICC, and local requirements.
- B. Arisfor WallGuard® may be applied by roller, trowel or spray.
- C. The base material should be approximately 3/16" to 1/8" thick. Additional layers may be applied to ensure mesh is uniformly covered and the desired finish is achieved.
- D. Apply one layer of Arisfor WallGuard® to substrate and then embed the mesh, working from the center to the edges, while mixture is still wet. Lightly use trowel to fully encapsulate mesh.
- E. Expansion joints are required where there are existing expansion joints in the substrate.

3.4 DRYING / CURING

- A. Dries to the touch in 4-8 hours



SECTION 09 24 23
Arisfor WallGuard®

- B. Cure and provide time between coats in accordance with ASTM C 926 and manufacturer's instructions.
- C. Provide sufficient moisture in the plaster mix by curing to permit continuous hydration of the cementitious materials.
- D. Allow sufficient time between coats to permit each coat to cure and develop sufficient strength to resist cracking or other physical damage before the next coat is applied.
- E. Where allowed by local jurisdictions, the IBC 'Alternative Method' may be used as the standard for time between coats and curing.

3.5 FIELD QUALITY CONTROL

- A. Architect or qualified third party will inspect the application at the following stages to confirm the Arisfor WallGuard® is being applied and cured as specified - and as indicated on the drawings.
 - 1. Completion of substrate installation, preparation, flashing and lathing.
 - 2. Completion of base/finish coat application.

3.6 CLEANING

- A. Remove and dispose of all temporary materials used to protect adjacent work and surrounding areas.
- B. Clean tools with water before product permanently adheres.
- C. Remove and clean from surfaces not intended to receive the Arisfor WallGuard®. Floors, windows, metal door frames or any surface not intended to be coated, should be wiped clean using a wet cloth within minutes of application to avoid permanent adhesion.

3.7 PROTECTION

- A. Protect installed products until completion of project.
- B. Touch-up, repair or replace damaged products before Substantial Completion.

3.8 LIMITATION

- A. Do not apply over expansion joints. Moving cracks/joints may reflect through finished product.

3.9 WARRANTY

- A. Upon request, at completion of installation, provide manufacturer's Limited Warranty.

END OF SECTION

(Rev. July 2015)